



**LEATMESPECIAL**  
GENUINE ITALIAN LEATHER FOR SNOBBISH CARS

TECHNICAL DATA SHEET

CODE **G202126** • PANTONE **2312U**

## AUTOMOTIVE AFTERMARKET LEATHER

### Caratteristiche tecniche

#### Technical specifications

|                              |   |
|------------------------------|---|
| Spessore (Thickness)         | 0,9 - 1,2 mm                                |
| Provenienza (Leather Origin) | Leatmespecial Italy Warehouse Ready to Ship |
| Tipologia (Leather types)    | Fiore corretto (Corrected grain)            |
| Tipo di concia (Tannage)     | Sali di cromo (Chrome tannage)              |
| Tipo di tintura (Dying)      | Tintura passante in botte (Through dying)   |

### Caratteristiche di solidità al colore

#### Colour Fastness specifications

|  | METODO DI PROVA<br>(Test method) | SPECIFICA<br>(detail)                           |
|--|----------------------------------|---|
| Resistenza agli sfregamenti a secco 1000 cicli consecutivi<br>(Dry rub fastness 1000 consecutive cycles)             | EN ISO 11640                     | min 4 scala dei grigi<br>(val 4 gray scale)     |
| Resistenza agli sfregamenti a umido 300 cicli consecutivi<br>(Wet rub fastness 300 consecutive cycles)               | EN ISO 11640                     | min 4 scala dei grigi<br>(val 4 gray scale)     |
| Resistenza all'abrasione 300 cicli consecutivi, Taber CS 10, 500 g<br>(Abrasion resistance 300 cycles, CS 10, 500 g) | ISO 17076                        | Nessuna visibile rottura<br>(No visible damage) |
| Solidità del colore alla luce<br>(fastness to light)   | IUF 402                          | min 4 scala dei blu<br>(val 4 blu scale)        |

### Caratteristiche fisiche

#### Physical specifications

|   | METODO DI PROVA<br>(Test method) | SPECIFICA<br>(detail)           |
|---|----------------------------------|---------------------------------|
| Adesione della rifinitura (Finishing adhesion)                            | EN ISO 11644                     | ≥ 4 N/cm (a secco)<br>(dry)     |
| Resistenza alle flessioni 25,000 cicli<br>(Flex resistance 25,000 cycles) | EN ISO 5402                      | nessuna rottura<br>(any damage) |
| Comportamento al fuoco (Flammability)                                     | ISO 3795 / FMVSS 302             | ≤ 100 mm/minute                 |
| Resistenza alle lacerazioni (Tear strength)                               | IUP 8                            | ≥ 15 N                          |

### Caratteristiche chimiche

#### Chemical specifications

|   |                             |
|---|-----------------------------|
| AZO-Coloranti (Direttiva 2002/61/CE)<br>(Azo-dyes Directive 2002/61/CE) | Assenti (< 30 ppm) (Absent) |
| Contenuto in PCP (PCP content)  | Assente (< 5 ppm) (Absent)  |

**LEATMESPECIAL**  
GENUINE ITALIAN LEATHER FOR SNOBBISH CARS

Quantificio 2 Esse srl  
Via Thomas Alva Edison, 9 | 47122 Forlì FC - ITALY  
Tel. +39 0543 750147



**MADE IN ITALY IS NOT AN OPINION.**